

09/869430

www.sughrue.com



SUGHRUE MION ZINN MACPEAK &amp; SEAS, PLLC

June 28, 2001

**BOX PCT**Commissioner for Patents  
Washington, D.C. 20231PCT/JP99/05654  
-filed October 14, 1999

Re: Application of Ryuji IWAKIRI (deceased), Ryoichi FUKAGAWA,  
Keisuke TANO, Daisuke TANIZAWA and Nobuhiko TSUDA  
THERMOSETTING POWDER COATING COMPOSITION  
**Assignee: DAIKIN INDUSTRIES, LTD.**  
Our Ref: Q65021

Dear Sir:

The following documents and fees are submitted herewith in connection with the above application for the purpose of entering the National stage under 35 U.S.C. § 371 and in accordance with Chapter II of the Patent Cooperation Treaty:

- ☒ an executed Declaration and Power of Attorney.
- ☒ an English translation of the International Application.
- ☒ an International Preliminary Examination Report (foreign language).
- ☒ an executed Assignment and PTO 1595 form.
- ☒ a Form PTO-1449 listing the ISR references, and a complete copy of each reference.
- ☒ a Preliminary Amendment.

It is assumed that copies of the International Application, the International Search Report, the International Preliminary Examination Report, and any Articles 19 and 34 amendments as required by § 371(c) will be supplied directly by the International Bureau, but if further copies are needed, the undersigned can easily provide them upon request.

Assignment for published patent application is: **DAIKIN INDUSTRIES, LTD.**

The Government filing fee is calculated as follows:

Total claims	<u>5</u>	-	20	=		x	\$18.00	=	\$0.00
Independent claims	<u>2</u>	-	3	=		x	\$80.00	=	\$0.00
Base Fee									\$860.00

**TOTAL FILING FEE**\$860.00**Recordation of Assignment**\$ 40.00**TOTAL FEE**\$900.00

Checks for the statutory filing fee of \$860.00 and Assignment recordation fee of \$40.00 are attached. You are also directed and authorized to charge or credit any difference or

JC03 Rec'd PGT/PTC 28 JUN 2001




# Sughrue

SUGHRUE MION ZINN MACPEAK & SEAS, PLLC

overpayment to Deposit Account No. 19-4880. The Commissioner is hereby authorized to charge any fees under 37 C.F.R. §§ 1.16, 1.17 and 1.492 which may be required during the entire pendency of the application to Deposit Account No. 19-4880. A duplicate copy of this transmittal letter is attached.

There is no claim to priority.

Respectfully submitted,



Abraham J. Rosner  
Registration No. 33,276

SUGHRUE, MION, ZINN,  
MACPEAK & SEAS, PLLC  
2100 Pennsylvania Avenue, N.W.  
Washington, D.C. 20037-3213  
Telephone: (202) 293-7060  
Facsimile: (202) 293-7860

Date: June 28, 2001

[illegible]

09/869430

JC03 Rec'd PCT/PTC 28 JUN 2001

**PATENT APPLICATION**

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

In re application of

Ryuji IWAKIRI, et al.

PCT/JP99/05654

Appln. No.: Unassigned

Group Art Unit: Unassigned

Confirmation No.: Unassigned

Examiner: Unassigned

Filed: June 28, 2001

For: THERMOSETTING POWDER COATING COMPOSITION

**PRELIMINARY AMENDMENT**

Commissioner for Patents  
Washington, D.C. 20231

Sir:

Prior to examination, please amend the above-identified application as follows:

**IN THE CLAIMS:**

**Please enter the following amended claims:**

3. (Amended) The powder coating composition of Claim 1, wherein said vinyl ester unit is vinyl versatate unit and/or vinyl benzoate unit.

**PRELIMINARY AMENDMENT**

**U.S. Appln. No. -- National Stage Entry of PCT/JP99/05654**

**REMARKS**

Entry and consideration of this Amendment is respectfully requested.

Respectfully submitted,



---

Abraham J. Rosner  
Registration No. 33,276

SUGHRUE, MION, ZINN,  
MACPEAK & SEAS, PLLC  
2100 Pennsylvania Avenue, N.W.  
Washington, D.C. 20037-3213  
Telephone: (202) 293-7060  
Facsimile: (202) 293-7860

Date: June 28, 2001

**PRELIMINARY AMENDMENT**

**U.S. Appln. No. -- National Stage Entry of PCT/JP99/05654**

**APPENDIX**

**VERSION WITH MARKINGS TO SHOW CHANGES MADE**

**IN THE CLAIMS:**

**The claims are amended as follows:**

3. (Amended) The powder coating composition of ~~Claim 1 or 2~~ Claim 1, wherein  
said vinyl ester unit is vinyl versatate unit and/or vinyl benzoate unit.

## DESCRIPTION

THERMOSETTING POWDER COATING COMPOSITION

5

## TECHNICAL FIELD

The present invention relates to a thermosetting powder coating composition which comprises a thermosetting fluorine-containing resin and a thermosetting polyester resin as resin components for the powder coating composition and gives well-balanced  
10 excellent weather resistance and appearance of a coating film.

## BACKGROUND ART

A thermosetting powder coating composition has been used widely in the field of coating for industrial use because it is free from an  
15 environmental problem since an organic solvent is not used and because it gives a coating film having excellent characteristics. Powder coating compositions such as an acrylic resin and polyester are known as such a thermosetting powder coating composition.

However for example, an acrylic resin powder coating  
20 composition has merits such as a relatively low cost and excellent appearance of a coating film, but weather resistance thereof is insufficient. Also there is a problem that in case where the same coating line is used also for other resin powder coating composition, an appearance of a coating film is lowered by mixing of a small amount of  
25 the other resin powder coating composition. Therefore the coating line must be isolated for each of the coating compositions.

A polyester powder coating composition has also merits such

09/869430-052804

as a relatively low cost, good pigment dispersibility and excellent appearance of a coating film, but there are problems that weather resistance thereof is more insufficient than the acrylic resin powder coating composition and is difficult to be used for coating for outdoor  
5 use.

As a powder coating composition being excellent in weather resistance, there is known a thermosetting fluorine-containing resin powder coating composition (JP-B-6-104792, JP-A-6-345822, JP-A-6-184243, etc.). However the thermosetting fluorine-containing resin  
10 powder coating composition is high in cost, insufficient in adhesion to a substrate and inferior in an appearance of a coating film, particularly smoothness thereof and also has a problem with storage stability because blocking easily occurs.

In order to eliminate those problems, studies have been made.  
15 For example, in case of a polyester powder coating composition, there are attempts that neopentyl glycol is used as a polyol component and isophthalic acid is used as a polycarboxylic acid component in order to enhance weather resistance (JP-A-9-71738, JP-A-11-100548). However when amounts of neopentyl glycol and isophthalic acid  
20 components are increased, weather resistance is enhanced though it is inferior as compared with the fluorine-containing resin, but there is a problem that a flexibility and also physical properties of a coating film are lowered.

There is a proposal to solve those problems by blending a  
25 fluorine-containing resin with a polyester resin (Japanese Patent No. 2886914). In that invention, a blend of a fluorine-containing resin having hydroxyl group and polyester resin having hydroxyl group is

disclosed. However in such a resin blend, adhesion and storage stability are improved, but a compatibility between a fluorine-containing polymer and a polyester polymer is insufficient, an appearance of a coating film is not improved and also weather resistance is not sufficient.

### DISCLOSURE OF INVENTION

In the present invention the above-mentioned problems, particularly a problem of enhancing and well balancing weather resistance and appearance of a coating film are solved by the following means.

Namely the present invention relates to a thermosetting powder coating composition which is prepared by using a fluorine-containing polymer and a polyester polymer together and contains a curing agent, wherein

the fluorine-containing polymer (A) comprising a fluoroolefin unit and vinyl ester unit and having a crosslinkable reactive group is used as a fluorine-containing polymer, or

the polyester polymer (I) containing isophthalic acid and/or 1,4-cyclohexane dicarboxylic acid as the essential component unit and having a crosslinkable reactive group is used as a polyester polymer.

Hereinafter the former invention is referred to as "Invention 1", and the latter invention is referred to as "Invention 2".

Invention 1 is a thermosetting powder coating composition comprising the above-mentioned specific fluorine-containing polymer (A), a polyester polymer (B) having a crosslinkable reactive group and a curing agent. Particularly it is preferable that a molecular weight of the



vinyl ester unit in the fluorine-containing polymer (A) is from 70 to 400 and that the above-mentioned vinyl ester unit is vinyl versatate unit and/or vinyl benzoate unit.

5 Invention 1 can enhance and well-balance weather resistance and appearance of the obtained coating film, can improve adhesion to a substrate and can provide a powder coating composition having excellent storage stability.

Further Invention 2 is a thermosetting powder coating composition comprising the above-mentioned specific polyester polymer (I), a fluorine-containing polymer (II) having a crosslinkable reactive group and a curing agent. It is preferable that the above-mentioned specific polyester polymer (I) is a polyester polymer containing isophthalic acid and/or 1,4-cyclohexane dicarboxylic acid as a polybasic acid component and a polyhydric alcohol as a polyol component, in which hydrogen at  $\beta$  position has been substituted by an alkyl group.

15 Invention 2 can enhance and well-balance weather resistance and appearance of the obtained coating film and further can provide a powder coating composition free from lowering of physical properties of the coating film, for example, flexibility.

20

#### BEST MODE FOR CARRYING OUT THE INVENTION

At first, Invention 1 is concretely explained below.

Invention 1 is characterized in that by mixing the thermosetting polyester polymer (B) to the thermosetting fluorine-containing polymer (A) comprising specific monomers, adhesion to a substrate, weather resistance and storage stability of the powder (anti-blocking property) are enhanced without lowering an appearance of a

coating film.

The thermosetting fluorine-containing polymer (A) to be used in Invention 1 comprises a fluoroolefin unit and a vinyl ester unit as the essential components.

5           Examples of the fluoroolefin are, for instance, tetrafluoroethylene, monofluoroethylene, trifluoroethylene, vinylidene fluoride, hexafluoropropylene, pentafluoropropylene, chlorotrifluoroethylene, and the like. The fluoroolefin can be optionally selected depending on characteristics required for a coating film and a  
10 combination with other copolymer component or a curing agent. Also two or more of those fluoroolefins can be used. Particularly preferable fluoroolefins are perfluoroolefins such as tetrafluoroethylene and hexafluoropropylene and chlorotrifluoroethylene from the viewpoint of copolymerizability and weather resistance.

15           The vinyl ester unit to be contained as the essential component has a function of lowering a melting point or a glass transition temperature of the fluorine-containing polymer and thus further enhancing workability at coating, a function of imparting physical properties such as a proper hardness, flexibility and gloss to  
20 the coating film and a function of enhancing a compatibility with the polyester resin.

As such a vinyl ester unit, one which has an unsaturated group being active to an extent of being copolymerizable with the fluoroolefin and does not lower weather resistance of the coating film  
25 remarkably is used. Examples thereof are one or two or more of vinyl acetate, vinyl propionate, vinyl n-butyrate, vinyl isobutyrate, vinyl valerate, vinyl pivalate, vinyl caproate, vinyl caprylate, vinyl caprate,

vinyl versatate, vinyl laurate, vinyl myristate, vinyl palmitate, vinyl stearate, vinyl benzoate, vinyl para-t-butyl benzoate, vinyl cyclohexanecarboxylate, vinyl monochloroacetate, vinyl adipate, vinyl acrylate, vinyl methacrylate, vinyl crotonate, vinyl sorbinate, vinyl cinnamate, vinyl undecylate, and the like. Among them, vinyl versatate and vinyl benzoate are preferable from the viewpoint of compatibility with the polyester resin.

It is preferable from the viewpoint of copolymerizability with the fluoroolefin that a molecular weight of the vinyl ester monomer is from 70 to 400, particularly 100 to 250.

A content of the vinyl ester unit is from 1 to 30 % by weight, preferably 5 to 25 % by weight based on the fluorine-containing polymer. If the content is more than that range, weather resistance is lowered, and if less than the mentioned range, a compatibility with the polyester resin is lowered.

The fluorine-containing polymer to be used in Invention 1 may be copolymerized with a comonomer as case demands. As such an optional monomer, ethylenically unsaturated compounds are suitable. Examples thereof are, for instance, alkyl vinyl ethers such as ethyl vinyl ether, propyl vinyl ether, butyl vinyl ether, isobutyl vinyl ether and cyclohexyl vinyl ether; alkyl allyl ethers such as ethyl allyl ether, propyl allyl ether, butyl allyl ether, isobutyl allyl ether and cyclohexyl allyl ether; alkyl allyl esters such as ethyl allyl ester, propyl allyl ester, butyl allyl ester, isobutyl allyl ester and cyclohexyl allyl ester; alkenes such as ethylene, propylene, butylene and isobutylene; acrylic acid and methacrylic acid; esters of acrylic acid or methacrylic acid such as ethyl acrylate, propyl acrylate, butyl acrylate, isobutyl acrylate, 2-ethylhexyl

acrylate, ethyl methacrylate, propyl methacrylate, butyl methacrylate, isobutyl methacrylate and 2-ethylhexyl methacrylate; partly fluorine-substituted compounds thereof; and the like. Those optional comonomers may be used solely or in combination of two or more thereof.

As the optional comonomer, vinyl and ally compounds or alkenes which have excellent copolymerizability with the fluoroolefin are used preferably. When allyl alkyl esters or vinyl or allyl alkyl ethers are used, a linear, branched or alicyclic alkyl group having about 2 to about 10 carbon atoms can be used suitably.

Examples of the crosslinkable reactive group of the thermosetting fluorine-containing polymer (A) to be used in Invention 1 are hydroxyl group, carboxyl group, amido group, amino group, mercapto group, glycidyl group, isocyanate group, and the like. Examples of a method for introducing such a crosslinkable reactive group into the copolymer are a method of copolymerizing a monomer having a crosslinkable reactive group, a method of decomposing a part of the copolymer, a method of reacting a reactive group of the copolymer with a compound giving a crosslinkable reactive group thereto, and the like.

Examples of the comonomer which can introduce a suitable crosslinkable reactive group by copolymerization are, for instance, monomers having hydroxyl group or a group which can be converted to hydroxyl group and having a double bond being copolymerizable with the fluoroolefin. Examples thereof are one or two or more of hydroxyalkyl vinyl ethers such as hydroxyethyl vinyl ether, hydroxypropyl vinyl ether, hydroxybutyl vinyl ether, hydroxyisobutyl

vinyl ether and hydroxycyclohexyl vinyl ether; esters of vinyl alcohol and hydroxyalkylcarboxylic acid such as vinyl hydroxyacetate, vinyl hydroxypropionate, vinyl hydroxybutyrate, vinyl hydroxyvalerate, vinyl hydroxyisobutyrate and vinyl hydroxycyclohexanecarboxylate; 5 hydroxyalkyl allyl ethers such as hydroxyethyl allyl ether, hydroxypropyl allyl ether, hydroxybutyl allyl ether, hydroxyisobutyl allyl ether and hydroxycyclohexyl allyl ether; hydroxyallyl esters such as hydroxyethyl allyl ester, hydroxypropyl allyl ester, hydroxybutyl allyl ester, hydroxyisobutyl allyl ester and hydroxycyclohexyl allyl ester; 10 hydroxyalkyl esters of acrylic acid or methacrylic acid such as 2-hydroxyethyl acrylate, hydroxypropyl acrylate, 2-hydroxyethyl methacrylate and hydroxypropyl methacrylate; partly fluorine-substituted compounds thereof; and the like. One or two or more thereof may be selected and used as a comonomer for introducing 15 hydroxyl group.

Examples of the comonomer having carboxyl group are, for instance,  $\alpha,\beta$ -unsaturated carboxylic acids such as acrylic acid, methacrylic acid, itaconic acid, fumaric acid, fumaric anhydride, crotonic acid, maleic acid, maleic anhydride and undecylenic acid and in 20 addition, fluorine-substituted monomer such as perfluorobutenoic acid, carboxyl alkyl allyl ether such as allyloxy propionic acid, and the like. Also examples of the comonomer having glycidyl group are, for instance, glycidyl (meth)acrylate, glycidyl vinyl ether, glycidyl allyl ether, and the like. Examples of the comonomer having amino group are, for instance, 25 amino alkyl vinyl ether, amino alkyl allyl ether, and the like. Examples of the comonomer having amido group are, for instance, (meth)acrylamide, methylolacrylamide, and the like. Examples of the

comonomer having nitrile group are, for instance, (meth)acrylonitrile, and the like. Examples of the comonomer having isocyanate group are, for instance, vinyl isocyanate, isocyanate ethyl acrylate, and the like. Examples of the comonomer having an activated halogen group are, for instance, vinyl chloride, vinylidene chloride, and the like.

It is preferable to use particularly a vinyl or allyl ether or ester compound as a comonomer for introducing a crosslinkable reactive group from the viewpoint of excellent copolymerizability with the fluoroolefin.

Example of the method for partly decomposing the copolymer is a method of copolymerizing a monomer having a hydrolyzable ester group after polymerization and then hydrolyzing the copolymer to generate carboxyl group in the copolymer. Also it is possible to form crosslinkage directly by transesterification in a curing reaction without carrying out ester hydrolysis mentioned above.

As the method for reacting a compound giving a crosslinkable reactive group into the copolymer, for example, a method of introducing carboxyl group by reacting a divalent carboxylic acid anhydride such as succinic anhydride with a fluorine-containing copolymer having hydroxyl group can be employed suitably.

From the above-mentioned point of view, examples of the thermosetting fluorine-containing polymer (A) are, for instance, tetrafluoroethylene/cyclohexyl vinyl ether/vinyl versatate/hydroxybutyl vinyl ether copolymer, tetrafluoroethylene/cyclohexyl vinyl ether/vinyl benzoate/hydroxybutyl vinyl ether copolymer, tetrafluoroethylene/vinyl p-t-butylbenzoate/hydroxybutyl vinyl ether copolymer, tetrafluoroethylene/hexafluoropropylene/ethylene/vinyl

versatate/hydroxybutyl vinyl ether copolymer,  
tetrafluoroethylene/hexafluoropropylene/ethylene/vinyl  
benzoate/hydroxybutyl vinyl ether copolymer,  
tetrafluoroethylene/hexafluoropropylene/ethylene/vinyl p-t-  
5 butylbenzoate/hydroxybutyl vinyl ether copolymer,  
chlorotrifluoroethylene/cyclohexyl vinyl ether/vinyl  
versatate/hydroxybutyl vinyl ether copolymer,  
chlorotrifluoroethylene/cyclohexyl vinyl ether/vinyl  
benzoate/hydroxybutyl vinyl ether copolymer, and the like.

10 It is desirable that the thermosetting fluorine-containing polymer (A) to be used for the thermosetting powder coating composition of Invention 1 has a fluorine content of not less than 10 % by weight. When the fluorine content is less than 10 % by weight, a coating film having a sufficient weather resistance cannot be obtained.

15 Also it is desirable that a MFR of the thermosetting fluorine-containing polymer (A) is within a range of from 0.1 to 100 g/10 min when measured at 100° to 180°C. When the MFR measured at 100°C of a low temperature side is less than 0.1 g/10 min, meltability of the resin at kneading with other additives such as a pigment is not sufficient, and  
20 thus color developing property, weather resistance and impact resistance of the obtained coating film are inferior. When the MFR measured at 180°C of a high temperature side is larger than 100 g/10 min, a viscosity of the resin at melt-kneading is lowered and the melt-kneading is not sufficient, and thus color developing property, weather  
25 resistance and impact resistance of the obtained coating film are also inferior.

Further it is desirable that the thermosetting fluorine-

containing polymer (A) has a glass transition temperature of 30° to 120°C. When the glass transition temperature is not more than 30°C, storage stability of the obtained coating composition is not sufficient. When exceeding 120°C, melt-kneading property is lowered, thereby  
5 making it impossible to sufficiently disperse other additives such as a pigment at the melt-kneading step.

In Invention 1, as far as the above-mentioned specific polymer (A) is used as a thermosetting fluorine-containing polymer, the thermosetting polyester polymer (B) which is another resin component  
10 for the powder coating composition is not limited particularly when the polymer (B) has excellent weather resistance. Known polyester polymers having crosslinkable reactive group can be used.

Examples of the crosslinkable reactive group to be introduced into the thermosetting polyester polymer (B) are hydroxyl  
15 group, carboxyl group, and the like. Hydroxyl group and carboxyl group can be introduced in an optional amount by adjusting a reacting mole ratio of a polycarboxylic acid component and polyol component. A hydroxyl value thereof is from 14 to 100 mgKOH/g, preferably 25 to 60 mgKOH/g, and an acid value is from 15 to 50 mgKOH/g.

20 Examples of the thermosetting polyester polymer (B) are those comprising a polycarboxylic acid component and a polyol component. Examples of the polycarboxylic acid component are aromatic polycarboxylic acid, aliphatic polycarboxylic acid or acid anhydride thereof, and for instance, isophthalic acid, phthalic anhydride,  
25 terephthalic acid, succinic anhydride, adipic acid, sebacic acid, azelaic acid, 1,4-cyclohexanedicarboxylic acid, tetrahydrophthalic anhydride, hexahydrophthalic anhydride, trimellitic anhydride, and the like.



Among those polycarboxylic acids, it is preferable to use polycarboxylic acids having a cyclic structure, particularly isophthalic acid and 1,4-cyclohexanedicarboxylic acid solely or in combination thereof from the viewpoint of enhancement of weather resistance.

5           As the polyol component, a polyol which has been used for synthesis of polyester can be used. Examples thereof are, for instance, aliphatic glycols such as ethylene glycol, diethylene glycol, propylene glycol, 1,4-butanediol, 1,6-hexanediol and 1,4-cyclohexanedimethanol. From the viewpoint of weather resistance, it is preferable to contain a  
10 polyol in which hydrogen at  $\beta$  position has been substituted by an alkyl group. Examples thereof are 2,2-dimethyl-1,3-propanediol (neopentyl glycol), 2-butyl-2-ethyl-1,3-propanediol, hydroxypivalyl hydroxypivalate, hydrogenated bisphenol A, 1,4-cyclohexanedimethanol, and the like. Also there are aromatic diols such as ethylene oxide adduct of bisphenol  
15 A and ethylene oxide adduct of bisphenol S and trivalent alcohols such as trimethylolpropane, glycerine and pentaerythritol as far as an amount thereof is small.

The thermosetting powder coating composition of Invention 1 comprises one or two or more of the above-mentioned thermosetting  
20 polyester polymers (B) and one or two or more of the specific fluorine-containing polymer (A) as the resin components. A mixing ratio (A)/(B) of the polymer (A) and the polymer (B) can be selected in a wide range of from 99/1 to 1/99 in a weight ratio, and is preferably from 99/1 to 50/50 from the viewpoint of an improvement in weather resistance of  
25 the polyester resin (B). When a proportion of the fluorine-containing polymer (A) is too small, a degree of enhancement of weather resistance is decreased. However when a specific polyester polymer (I) mentioned

hereinafter is used as the polyester polymer (B), even if the ratio (A)/(B) is 1/99 to 50/50, preferably 25/75 to 50/50, weather resistance and appearance of a coating film which are balanced in conformity with a purpose can be obtained.

5           The thermosetting powder coating composition of Invention 1 can be prepared by adding a curing agent to the above-mentioned resin components. In addition, various additives which are used usually for a powder coating can be added. Since those curing agent and additives can be used also in Invention 2, explanation thereof is made hereinafter.  
10 Further a preparation process of the powder coating composition, article to be coated with the composition and coating method are common to those of Invention 2, and therefore are explained hereinafter.

Then Invention 2 is concretely explained below.

15           Invention 2 is characterized in that a specific thermosetting polyester polymer (I) containing isophthalic acid and/or 1,4-cyclohexanedicarboxylic acid as the essential component unit and having a crosslinkable reactive group is used as the thermosetting polyester polymer.

20           The polyester polymer (I) containing isophthalic acid and/or 1,4-cyclohexanedicarboxylic acid as the essential component unit is one in which isophthalic acid and/or 1,4-cyclohexanedicarboxylic acid are used as a polybasic acid component. Examples of usable polybasic acids in addition to the above-mentioned specific polybasic acids are aromatic polycarboxylic acids, aliphatic polycarboxylic acids, acid  
25 anhydrides thereof, and the like. Examples thereof are, for instance, phthalic anhydride, terephthalic anhydride, succinic anhydride, adipic acid, sebacic acid, azelaic acid, tetrahydrophthalic anhydride,

hexahydrophthalic anhydride, trimellitic anhydride, and the like. Among those polycarboxylic acids to be used together, from the viewpoint of enhancing a mechanical strength such as impact resistance, it is preferable to use aromatic polycarboxylic acids, particularly  
5 terephthalic acid as a polybasic acid component to be added solely.

On the other hand from the viewpoint of further enhancing weather resistance, it is preferable to use, as a polyol component, a polyhydric alcohol, in which hydrogen at  $\beta$  position has been substituted with an alkyl group. Examples thereof are 2,2-dimethyl-1,3-  
10 propanediol (neopentyl glycol), 2-butyl-2-ethyl-1,3-propanediol, hydroxypivalyl hydroxypivalate, hydrogenated bisphenol A, 1,4-cyclohexanedimethanol, and the like. From the viewpoint of compatibility with the fluorine-containing resin having a crosslinkable reactive group, 2,2-dimethyl-1,3-propanediol and 2-butyl-2-ethyl-1,3-  
15 propanediol are preferable. Further polyols which have been used for synthesis of polyester can be used together. Examples thereof are, for instance, aliphatic glycols such as ethylene glycol, diethylene glycol, propylene glycol, 1,4-butanediol, 1,6-hexanediol and 1,4-cyclohexanedimethanol; aromatic diols such as ethylene oxide adduct of  
20 bisphenol A and ethylene oxide adduct of bisphenol S; and trivalent alcohols such as trimethylolpropane, glycerine and pentaerythritol. Among them, it is preferable to use 2,2-dimethyl-1,3-propanediol and 2-butyl-2-ethyl-1,3-propanediol solely or in combination thereof from the viewpoint of enhancing weather resistance and compatibility with  
25 the fluorine-containing polymer (II) having a crosslinkable reactive group.

As case demands, oxycarboxylic acid unit such as 4-hydroxy

benzoate or  $\epsilon$ -caprolactone may be contained as a component unit of the polyester polymer (I).

It is necessary that the polyester polymer (I) to be used in Invention 2 has a limiting viscosity of from 0.15 to 0.40 dl/g. The limiting viscosity is preferably from 0.20 to 0.35 dl/g. When the limiting viscosity of the polyester polymer (I) is less than 0.15 dl/g, anti-blocking property of the powder coating composition tends to be lowered. When exceeding 0.40 dl/g, pulverizability of the resin tends to be lowered.

It is desirable that the polyester polymer (I) to be used in Invention 2 has a hydroxyl value of from 14 to 100 mgKOH/g, preferably 25 to 60 mgKOH/g or an acid value of from 15 to 50 mgKOH/g. When the hydroxyl value is less than 14 mgKOH/g or the acid value is less than 15 mgKOH/g, there is a tendency that there arise a large unevenness on a surface of a coating film and smoothness is lowered. When the hydroxyl value exceeds 100 mgKOH/g, a mechanical strength of the coating film tends to be lowered. Or when the acid value exceeds 50 mgKOH/g, an adding amount of the epoxy resin curing agent must be increased and thereby weather resistance of the coating film tends to be lowered.

The polyester polymer (I) of Invention 2 can be prepared by the method of carrying out esterification or transesterification of the above-mentioned polybasic acid component and polyol component (including ester-forming derivative thereof) as starting materials at a temperature of from 200° to 280°C by usual method and then carrying out a polycondensation reaction under reduced pressure of not more than 5 hPa at a temperature of 200° to 300°C, preferably 230° to 290°C

until a specific limiting viscosity is reached, thereby giving a polyester polymer having a high polymerization degree. Subsequently to the polyester polymer is added an alcohol component or carboxylic acid component, and a depolymerization reaction is carried out at a  
5 temperature of from 180° to 300°C, preferably 220° to 280°C until a specific limiting viscosity and hydroxyl value or acid value are obtained. Thus the polyester polymer (I) can be prepared.

Also the polyester polymer (I) can be prepared by carrying out esterification or transesterification by usual method and then carrying  
10 out a polycondensation reaction under atmospheric pressure or under reduced pressure of from about 50 hPa to about 100 hPa at a temperature of from 200° to 300°C, preferably 230° to 290°C until a specific limiting viscosity and hydroxyl value or acid value are obtained.

Examples of the polybasic acid component to be used for the  
15 above-mentioned depolymerization reaction are dicarboxylic acids such as isophthalic acid, phthalic acid and phthalic anhydride and polycarboxylic acids having three or more functional groups such as trimellitic acid, trimellitic anhydride and pyromellitic acid.

Also in the esterification, transesterification and  
20 polycondensation reaction, known reactive catalysts, and the like can be used.

Examples of preferable thermosetting polyester polymer (I) are, for instance, a copolycondensation product of isophthalic acid and neopentyl glycol, a copolycondensation product of isophthalic acid,  
25 terephthalic acid and neopentyl glycol, a copolycondensation product of isophthalic acid, terephthalic acid, neopentyl glycol and ethylene glycol, a copolycondensation product of 1,4-cyclohexane dicarboxylic acid and

neopentyl glycol, a copolycondensation product of 1,4-cyclohexane dicarboxylic acid, terephthalic acid and neopentyl glycol, a copolycondensation product of 1,4-cyclohexane dicarboxylic acid, terephthalic acid, neopentyl glycol and ethylene glycohol, and the like.

5 Among them, particularly from the viewpoint of excellent weather resistance and good compatibility with the fluorine-containing polymer (II), the copolycondensation product of isophthalic acid, terephthalic acid and neopentyl glycol and the copolycondensation product of 1,4-cyclohexane dicarboxylic acid, terephthalic acid and neopentyl glycol are  
10 preferable.

Examples of the fluorine-containing polymer (II) to be mixed to the thermosetting polyester polymer (I) are known polymers, for instance, those described in JP-B-6-104792, JP-A-6-345822, JP-A-6-184243, etc.

15 Examples thereof are, for instance, polymers comprising a fluoroolefin unit as an essential component and obtained by copolymerizing a compound having an unsaturated bond copolymerizable with the fluoroolefin. Examples of the fluoroolefin are, for instance, tetrafluoroethylene, monofluoroethylene, trifluoroethylene,  
20 vinylidene fluoride, hexafluoropropylene, pentafluoropropylene, chlorotrifluoroethylene, and the like. The fluoroolefin can be optionally selected depending on characteristics required for the coating film and a combination with other copolymer component or a curing agent. Also two or more of those fluoroolefins can be used. From the viewpoint of  
25 copolymerizability and weather resistance, particularly preferable fluoroolefins are perfluoroolefins such as tetrafluoroethylene and hexafluoropropylene and chlorotrifluoroethylene.

In Invention 2, from the viewpoint of compatibility with the polyester polymer and weather resistance, it is preferable to use the thermosetting fluorine-containing polymer (IIa) having a crosslinkable reactive group as the fluorine-containing polymer (II). Examples of the crosslinkable reactive group contained in the thermosetting fluorine-containing polymer are hydroxyl group, carboxyl group, amido group, amino group, mercapto group, glycidyl group, isocyanate group, and the like. Examples of a method for introducing such a crosslinkable reactive group into the copolymer are a method of copolymerizing a monomer having a crosslinkable reactive group, a method of decomposing a part of the copolymer, a method of reacting a reactive group of the copolymer with a compound giving a crosslinkable reactive group thereto, and the like.

Examples of the comonomer which can introduce a suitable crosslinkable reactive group by copolymerization are, for instance, monomers having hydroxyl group or a group which can be converted to hydroxyl group and having a double bond being copolymerizable with the fluoroolefin. Examples thereof are one or two or more of hydroxyalkyl vinyl ethers such as hydroxyethyl vinyl ether, hydroxypropyl vinyl ether, hydroxybutyl vinyl ether, hydroxyisobutyl vinyl ether and hydroxycyclohexyl vinyl ether; esters of vinyl alcohol and hydroxyalkylcarboxylic acid such as vinyl hydroxyacetate, vinyl hydroxypropionate, vinyl hydroxybutyrate, vinyl hydroxyvalerate, vinyl hydroxyisobutyrate and vinyl hydroxycyclohexanecarboxylate; hydroxyalkyl allyl ethers such as hydroxyethyl allyl ether, hydroxypropyl allyl ether, hydroxybutyl allyl ether, hydroxyisobutyl allyl ether and hydroxycyclohexyl allyl ether; hydroxyalkyl allyl esters such as

hydroxyethyl allyl ester, hydroxypropyl allyl ester, hydroxybutyl allyl ester, hydroxyisobutyl allyl ester and hydroxycyclohexyl allyl ester; hydroxyalkyl esters of acrylic acid or methacrylic acid such as 2-hydroxyethyl acrylate, hydroxypropyl acrylate, 2-hydroxyethyl methacrylate and hydroxypropyl methacrylate; partly fluorine-substituted compounds thereof; and the like. One or two or more thereof may be selected and used as a comonomer for introducing hydroxyl group.

Examples of the comonomer having carboxyl group are, for instance,  $\alpha,\beta$ -unsaturated carboxylic acids such as acrylic acid, methacrylic acid, itaconic acid, fumaric acid, fumaric anhydride, crotonic acid, maleic acid, maleic anhydride and undecylenic acid and in addition, carboxyl alkyl allyl ether such as allyloxy propionic acid, fluorine-substituted monomer such as perfluorobutenoic acid, and the like. Also examples of the comonomer having glycidyl group are, for instance, glycidyl (meth)acrylate, glycidyl vinyl ether, glycidyl allyl ether, and the like. Examples of the comonomer having amino group are, for instance, amino alkyl vinyl ether, amino alkyl allyl ether, and the like. Examples of the comonomer having amido group are, for instance, (meth)acrylamide, methylolacrylamide, and the like. Examples of the comonomer having nitrile group are, for instance, (meth)acrylonitrile, and the like. Examples of the comonomer having isocyanate group are, for instance, vinyl isocyanate, isocyanate ethyl acrylate, and the like. Examples of the comonomer having an activated halogen group are, for instance, vinyl chloride, vinylidene chloride, and the like.

It is preferable to use particularly a vinyl or allyl ether or ester compound as a comonomer for introducing a crosslinkable reactive



group from the viewpoint of excellent copolymerizability with the fluoroolefin.

Example of the method for partly decomposing the copolymer is a method of copolymerizing a monomer having a hydrolyzable ester group after polymerization and then hydrolyzing the copolymer to generate a carboxyl group in the copolymer. Also it is possible to form crosslinkage directly by transesterification in a curing reaction without carrying out ester hydrolysis mentioned above.

As the method for reacting the copolymer with a compound giving a crosslinkable reactive group thereto, for example, a method of introducing carboxyl group by reacting a divalent carboxylic acid anhydride such as succinic anhydride with a fluorine-containing copolymer having hydroxyl group can be employed suitably.

In addition to the above-mentioned fluoroolefin unit and the unit having a crosslinkable reactive group, a comonomer copolymerizable with those two components can be copolymerized in the thermosetting fluorine-containing polymer (IIa) to be used in Invention 2, in order to reduce a melting point or a glass transition temperature of the fluorine-containing polymer for further enhancing workability at coating and imparting physical properties such as proper hardness, flexibility and gloss to the coating film. Example of such an optional comonomer is one which has an unsaturated group being active to an extent of being able to be copolymerized with the fluoroolefin and does not lower weather resistance of the coating film remarkably.

Suitable examples of such an optional comonomer are ethylenically unsaturated compounds, for instance, alkyl vinyl ethers such as ethyl vinyl ether, propyl vinyl ether, butyl vinyl ether, isobutyl

vinyl ether and cyclohexyl vinyl ether; esters of vinyl alcohol and alkylcarboxylic acid such as vinyl acetate, vinyl propionate, vinyl butyrate, vinyl isobutyrate, vinyl valerate and vinyl cyclohexanecarboxylate; alkyl allyl ethers such as ethyl allyl ether, propyl allyl ether, butyl allyl ether, isobutyl allyl ether and cyclohexyl allyl ether; alkyl allyl esters such as ethyl allyl ester, propyl allyl ester, butyl allyl ester, isobutyl allyl ester and cyclohexyl allyl ester; alkenes such as ethylene, propylene, butylene and isobutylene; acrylic acid and methacrylic acid; esters of acrylic acid or methacrylic acid such as ethyl acrylate, propyl acrylate, butyl acrylate, isobutyl acrylate, 2-ethylhexyl acrylate, ethyl methacrylate, propyl methacrylate, butyl methacrylate, isobutyl methacrylate and 2-ethylhexyl methacrylate; partly fluorine-substituted compounds thereof; and the like. Those optional comonomers may be used solely or in combination of two or more thereof.

Among them, vinyl or allyl compounds or alkenes being excellent in copolymerizability with the fluoroolefin are used preferably as the optional comonomer. In case of using vinyl or allyl alkyl esters or alkyl ethers, a linear, branched or alicyclic alkyl group having about 2 to about 10 carbon atoms can be preferably used as an alkyl group.

From the above-mentioned point of view, examples of the thermosetting fluorine-containing polymer are, for instance, tetrafluoroethylene/cyclohexyl vinyl ether/isobutyl vinyl ether/hydroxybutyl vinyl ether copolymer, tetrafluoroethylene/isobutylene/hydroxybutyl vinyl ether copolymer, tetrafluoroethylene/hexafluoropropylene/ethylene/hydroxybutyl vinyl ether copolymer,

Examples of the thermosetting fluorine-containing polymer (IIa) which can be used particularly suitably in Invention 2 are copolymers comprising a perfluoroolefin such as tetrafluoroethylene or hexafluoropropylene and a vinyl ether and/or vinyl ester as the essential components. When such a resin is used, from the viewpoint of excellent adhesion and moisture permeability thereof, there can be obtained a higher effect of preventing rust of metallic substrate.

Also it is desirable that a MFR of the thermosetting fluorine-  
25 containing polymer (IIa) is within a range of from 0.1 to 100 g/10 min  
when measured at 100° to 180°C. When the MFR measured at 100°C of  
a low temperature side is less than 0.1 g/10 min, meltability of the resin

at kneading with other additives such as a pigment is not sufficient, and color developing property, weather resistance and impact resistance of the obtained coating film are inferior. When the MFR measured at 180°C of a high temperature side is larger than 100 g/10 min, a viscosity of the resin at melt-kneading is lowered and the melt-kneading is not sufficient, and thus color developing property, weather resistance and impact resistance of the obtained coating film are also inferior.

Further it is desirable that the thermosetting fluorine-containing polymer (IIa) has a glass transition temperature of from 30° to 120°C. When the glass transition temperature is not more than 30°C, storage stability of the obtained coating composition is not sufficient. When exceeding 120°C, melt-kneading property is lowered, thereby making it impossible to sufficiently disperse other additive such as a pigment at the melt-kneading step.

The resin components of the thermosetting powder coating composition of Invention 2 comprise one or two or more of the thermosetting polyester polymers (I) and one or two or more of the fluorine-containing polymers (II). A mixing ratio (I)/(II) of the polymer (I) to the polymer (II) can be selected in a wide range of from 99/1 to 1/99 in a weight ratio. From the viewpoint of improving weather resistance of the polyester polymer (I), the mixing ratio is preferably from 50/50 to 1/99. If the proportion of the fluorine-containing polymer (II) decreases, an effect of enhancing weather resistance is lowered. If the proportion of the fluorine-containing polymer (II) increases, there is a tendency that an appearance such as smoothness and gloss and flexibility of the coating film are lowered and workability at coating is lowered. In case where physical properties (for example, flexibility) of the coating film are

intended to be improved by the polyester polymer (I), the mixing ratio (I)/(II) of the polymer (I) to the polymer (II) may be from 99/1 to 50/50. Further in case where the above-mentioned fluorine-containing polymer (A) is used, even when the ratio is in a range of from 75/25 to 50/50, a  
5 coating film having properly balanced weather resistance and appearance can be obtained.

The thermosetting powder coating compositions of Invention 1 and Invention 2 can be prepared by blending a curing agent to the above-mentioned resin components.

10 As a curing agent, those which have been used for thermosetting polyester resin powder coating composition and/or thermosetting fluorine-containing resin powder coating composition can be used. Examples thereof are, for instance, blocked isocyanate compound, acid anhydrides, polyamine compounds, glycidyl  
15 compounds, isocyanurate compounds, polybasic acids, and the like. An adding amount thereof is one corresponding to an amount of the crosslinkable reactive group of the polymer, preferably 0.8 to 1.2 equivalents.

In addition, various additives which are usually used for a  
20 powder coating, for example, a pigment, filler, ultraviolet ray absorber, leveling agent, flowability control agent, antioxidant, heat deterioration preventing agent, gloss control agent, electric charge control agent, foaming preventing agent, and the like may be blended optionally. Among such third components, it is preferable to use those containing  
25 no chlorine.

Examples of the pigment are, for instance, one or two or more of inorganic pigments such as titanium dioxide, iron oxide red, yellow

iron oxide and carbon black; organic pigments such as phthalocyanine blue, phthalocyanine green, quinacridone red pigment and isoindolenone yellow pigment; extender pigments such as talc, silica and calcium carbonate; metal powders such as aluminum powder and stainless steel powder; mica powder; and the like. Also it is preferable that a rust inhibiting pigment represented by pyrophosphoric acid or tripolyphosphate is blended.

The thermosetting powder coating composition can be prepared in the same manner as in the known methods for preparing thermosetting powder coating compositions by dry-blending each component, melt-kneading and then pulverizing. As case demands, the third components to be added may be previously blended to the resin component or curing agent. An average particle size of the powder coating composition is usually not more than 400  $\mu\text{m}$ .

Examples of a substrate to be coated are a metallic substrate, plastic substrate, rubber substrate, ceramic substrate, substrate made of natural material, and the like. Examples of the metallic substrate are substrates of iron, aluminum, stainless steel, copper, zinc or alloys thereof, for instance, stainless steel and brass.

The coating can be carried out, for example, with a commercially available electrostatic coating machine or fluidized bed coating machine. After coating uniformly, a coating film is formed by baking with a hot air oven, infrared ray oven, induction heater, or the like.

Invention 1 and Invention 2 are then explained by means of examples and preparation examples, but the present invention is not limited to them.

## PREPARATION EXAMPLES 1 to 6

(Synthesis of thermosetting polyester polymer)

An esterification reactor was charged with starting compounds in amounts (part by mole) shown in Table 1, and esterification was carried out at a pressure of from 0.05 to 0.25 MPaG at 200° to 260°C for four hours. After the obtained esterified product was transferred into a polycondensation reactor, antimony trioxide was added thereto in an amount of  $4 \times 10^{-4}$  mole per 1 mole of acid component and a pressure inside the reactor was decreased to 0.4 hPa, followed by polycondensation reaction at 280°C for three hours. Thus a polyester resin having a limiting viscosity of 0.45 dl/g was obtained. Then to the polyester resin was added a depolymerization agent in an amount (part by mole) shown in Table 1, and a depolymerization reaction was carried out at 270°C at atmospheric pressure for one hour to give a polyester resin having characteristic values shown in Table 1. Characteristic values of the polyester polymers were obtained by the following methods.

(a) Limiting viscosity: Measurement was made at 20°C by using a solvent comprising a mixture of phenol and tetrachloroethane in an equivalent weight.

(b) Hydroxyl value: After acetylation of the resin with acetic anhydride, a hydroxyl value was obtained by titration with a methanol solution of potassium hydroxide.

(c) Acid value: After 0.5 g of the resin was dissolved in 50 ml of a solvent comprising a mixture of dioxane/diluted water = 10/1 (in weight ratio) and reflux by heating was carried out, an acid value was obtained by titration with a 0.1 N methanol solution of potassium hydroxide.

- (d) Softening temperature: The resin pulverized into a size of 60 to 100 mesh was put in a glass tube of 2.5 mm diameter × 150 mm length having a bottom in an amount up to a height of 30 mm from the bottom and the resin-filled part of the tube was dipped in an oil bath, followed by
- 5 heating at a rate of 1°C/min. A temperature where the resin begins to be liquefied is determined with naked eyes to give a softening temperature.

Abbreviations in Table 1 represent the following compounds.

IPA: Isophthalic acid

- 10 CHDA: 1,4-Cyclohexane dicarboxylic acid

TPA: Terephthalic acid

NPG: Neopentyl glycol

EG: Ethylene glycol

TMP: Trimethylolpropane

- 15 GC: Glycerine

TMA: Trimellitic acid



TABLE 1

Polyester polymer	Preparation Example					
	1	2	3	4	5	6
Starting compound						
IPA	80		60		80	
CHDA		80				
TPA	20	20	40	100	20	100
NPG	145	145			135	
EG			145	145		135
Depolymerization agent						
TMP	2	2		3		
GC			3	2		
NPG	2	2				
IPA					4	
TMA					4	4
Characteristics of resin						
Limiting viscosity (dl/g)	0.28	0.31	0.33	0.29	0.21	0.29
Hydroxyl value (mgKOH/g)	24	25	22	30		
Acid value (mgKOH/g)					47	34
Softening temperature (°C)	79	80	80	82	78	83
Abbreviation of polyester polymer	I-1	I-2	I-3	I-4	I-5	I-6

## PREPARATION EXAMPLE 7

(Preparation of thermosetting fluorine-containing polymer)

5 A 300-ml pressure resistant stainless steel reactor with a stirrer was charged with 157 g of t-butanol, 28 g of cyclohexyl vinyl ether (c-HxVE), 11 g of VeoVa9 (vinyl versatate available from Shell Chemical Co., Ltd.), 11 g of 4-hydroxybutyl vinyl ether (HBVE), 1 g of potassium carbonate and 0.07 g of azobisisobutyronitrile (AIBN), and dissolved air was removed by solid deaeration with liquid nitrogen. Then 50 g of chlorotrifluoroethylene (CTFE) was introduced, and the reactor  
10 temperature was slowly increased. A reaction was continued with stirring while maintaining the temperature at 65°C. Ten hours after, the reactor was cooled with water and the reaction was stopped. After cooling to room temperature, un-reacted monomer was released and the reaction was terminated. Then the reactor was heated up to 60°C, and  
15 a dispersing medium was removed under reduced pressure of 1 mmHg over 24 hours to give a thermosetting fluorine-containing copolymer (II-1). The obtained fluorine-containing copolymer was a copolymer of chlorotrifluoroethylene/cyclohexyl vinyl ether/VeoVa9/4-hydroxybutyl vinyl ether which were nearly the same components as the starting  
20 monomers. A glass transition temperature of the copolymer was 48°C, a melt viscosity MFR measured at 140°C was 10 g/10 min, and a hydroxyl value was 54 mgKOH/g.

The thermosetting fluorine-containing polymer (II-1) was pulverized with an impact hammer mill to be formed into a powder.

25

## PREPARATION EXAMPLES 8 to 9

Thermosetting fluorine-containing polymers shown in Table

2 were prepared in the same manner as in Preparation Example 7 except that monomer mixtures shown in Table 2 were used and amounts of a solvent (t-butanol) and polymerization initiator (AIBN) were changed optionally.

5           The obtained thermosetting fluorine-containing polymers were pulverized with an impact hammer mill to be formed into a powder.

#### PREPARATION EXAMPLE 10

After a 4,000-ml stainless steel autoclave was charged with  
10 760 g of deionized water and 7.6 g of potassium carbonate, increasing of a pressure inside the autoclave with nitrogen and deairing were repeated three times to remove dissolved oxygen. Then the autoclave was charged with 580 g of chlorofluoroethane (HCFC141b), 340 g of hexafluoropropene (HFP), 3.1 g of HBVE and 2.1 g of vinyl benzoate  
15 (VBz) under reduced pressure, and a temperature inside the autoclave was adjusted to 35°C. Further the pressure was adjusted to become 0.96 MPa with a monomer mixture of tetrafluoroethylene (TFE)/ethylene (Et) in a % by mole ratio of 82/18. Then 23 g of 25 % isobutyryl peroxide solution of flon 225 was introduced to initiate a reaction.  
20 Since the pressure lowered with advance of the reaction, a monomer mixture of TFE/Et/HFP in a % by mole ratio of 45/39/16 was supplied continuously to maintain the pressure inside the autoclave at 0.96 MPa. The reaction was carried out for eight hours while continuously supplying 15.8 g of HBVE and 11.3 g of VBz and adding 12 g of 25 %  
25 isobutyryl peroxide solution of flon 225 every six hours. Then the temperature and pressure inside the autoclave were lowered to ordinary temperature and atmospheric pressure to terminate the reaction. The

obtained solid was washed and dried to give 126 g of a white powder of fluorine-containing copolymer (II-4). The obtained fluorine-containing copolymer was a copolymer comprising TFE/HFP/Et/VBz/HBVE (41/24/14/10/11 % by weight). A glass transition temperature thereof was 40°C, a melt viscosity MFR measured at 140°C was 120 g/10 min, and a hydroxyl value was 53 mgKOH/g.

The obtained fluorine-containing copolymer was pulverized with an impact hammer mill.

10

#### PREPARATION EXAMPLE 11

A fluorine-containing polymer was prepared in the same manner as in Preparation Example 7 except that the monomer mixture shown in Table 2 was used. 100 Parts of the obtained polymer was dissolved in 100 parts of xylene, and 5.0 parts of succinic anhydride and 0.05 part of triethylbenzyl ammonium chloride were added thereto. The mixture was heated to 100°C in a four-neck flask provided with a stirrer and reacted with stirring for three hours, followed by cooling to terminate the reaction. Then the mixture was heated to 60°C and the solvent was removed under reduced pressure of 1 mmHg over 24 hours to give a thermosetting fluorine-containing copolymer (II-5) having carboxyl group.

15  
20

The obtained thermosetting fluorine-containing polymer was pulverized with an impact hammer mill to be formed into a powder.

Abbreviations in Table 2 represent the following compounds.

25 CTFE: Chlorotrifluoroethylene

TFE: Tetrafluoroethylene

HFP: Hexafluoropropylene



TABLE 2

Fluorine-containing polymer	Preparation Example				
	7	8	9	10	11
Monomer components (% by weight)					
CTFE	50	51	50	-	50
TFE	-	-	-	41	-
HFP	-	-	-	24	-
Et	-	-	-	14	-
c-HxVE	28	25	28	-	25
Veova9	11	-	-	-	-
VBz	-	10	-	10	5
HBVE	11	14	11	11	20
EVE	-	-	11	-	-
Total	100	100	100	100	100
Physical properties of polymer					
Hydroxyl value (mgKOH/g)	54	68	54	53	46.9
Acid value (mgKOH/g)	-	-	-	-	26.7
Glass transition temperature (°C)	48	45	45	40	42
MFR (g/10 min)	10	55	9	120	20
Abbreviation of fluorine-containing polymer	II-1	II-2	II-3	II-4	II-5

### EXAMPLE 1

- 41.8 Parts of the thermosetting polyester polymer powder (I-1) prepared in Preparation Example 1, 17.9 parts of the thermosetting fluorine-containing polymer (II-1) prepared in Preparation Example 7, 9.8 parts of a curing agent ( $\epsilon$ -caprolactam-blocked isocyanate, B-1530 available from Hüls Co., Ltd.), 30 parts of a pigment (titanium dioxide)

and 0.5 part of a leveling agent (MODAFLOW available from Monsanto Chemical Co., Ltd.) were dry-blended in Henschel mixer (available from Mitsui Kakoki Kabushiki Kaisha) for one minute. Then the mixture was melt-kneaded at 100°C with an extrusion kneader (Buss Co-kneader PR-46 available from Buss Co., Ltd.), and after cooled, pulverized with an impact hammer mill. The obtained powder was classified with a 150 mesh screen to give a thermosetting polyester resin powder coating composition.

The powder coating composition was coated on a 150 × 75 × 1 mm steel plate subjected to zinc phosphate treatment (thickness: 0.8 mm) by using a corona discharge type powder coating gun (GX3300 available from Onoda Cement Kabushiki Kaisha) at an applied voltage of 40 kV, and then baking was carried out at 190°C for 20 minutes to give a coated plate for testing. The following tests were carried out by using the coated plate. The results are shown in Table 3.

Thickness of cured coating film:

A thickness was measured with an eddy-current instrument EL10D for measuring thickness (available from Kabushiki Kaisha Sanko Denshi Kenkyusho).

Appearance of coating film:

When light of fluorescent lamp is reflected on a coating film, a shape of light reflected on a surface of the coating film is evaluated with naked eyes.

A: No distortion.

B: Slight distortion.

C: Apparent distortion.

D: Large distortion.

Gloss:

A specular reflectivity at an angle of 60 degrees is measured according to JIS K 5400 6.7.60.

Weather resistance:

5 After an accelerated weather resistance test is carried out for 2,000 hours with I-SUPER UV tester Model W-13 (Light/Dew/Rest = 11/11/1 HR is assumed to be one cycle) available from Iwasaki Electric Co., Ltd. according to JIS K5400 9.8.1, a gloss retention (a ratio of gloss after the test to initial gloss) is measured.

10 Flexibility:

A bending test is carried out according to AAMA605.

Adhesive property:

A coated plate is dipped in boiling water for two hours, and then adhesive property is evaluated by a cross-cut test according to JIS  
15 K5400 8.5.1.

Pulverizability:

After the pulverization, a proportion of particles having a particle size of not less than 400  $\mu\text{m}$  based on the total particles is measured, and pulverizability is evaluated by the following criteria.

20 A: 0 %

B: < 1 %

C: 1 to 10 %

D: > 10 %

Anti-blocking property:

25 15 Grams of the powder coating composition is put in a test tube of 40 mm diameter and allowed to stand at 35°C for 240 hours while applying a load of 20  $\text{g}/\text{cm}^2$  thereon. Then the powder is taken



out and a flowability and a state of blocking thereof are evaluated by the following criteria.

A: No blocking is recognized at all, and there is no change in flowability.

B: A flowability is lowered slightly.

5 C: Blocking is partly recognized.

D: Powder is wholly formed into a mass.

#### EXAMPLES 2 to 12

10 Thermosetting powder coating compositions comprising components shown in Table 3 were prepared and coated in the same manner as in Example 1, and various tests were carried out. The results are shown in Table 3.

TGIC in Tables 3, 4 and 5 represents triglycidyl isocyanurate.

TABLE 3

	Ex. 1	Ex. 2	Ex. 3	Ex. 4
Components of powder coating composition (part by weight)				
Fluorine-containing polymer (A)				
II-1	17.9	34.5		
II-2			17.6	33.3
II-4				
II-5				
Polyester polymer (B)				
I-1	41.8	23.0	41.0	22.2
I-4				
I-5				
I-6				
Curing agent				
B1530	9.8	12.0	10.0	12.1
TGIC				
Pigment	30	30	30	30
Leveling agent	0.5	0.5	0.5	0.5
(A)/(B)	30/70	60/40	30/70	60/40

- continued -

- continued -

Ex. 5	Ex. 6	Ex. 7	Ex. 8	Ex. 9	Ex. 10	Ex. 11	Ex. 12
		17.6	34.1				
17.9	34.6			19.4	39.2	19.7	39.5
41.8	23.0						
		41.0	22.8				
				45.2	26.1		
						45.9	26.4
9.5	11.9	10.9	12.6				
				4.9	4.2	3.9	3.6
30	30	30	30	30	30	30	30
0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
30/70	60/40	30/70	60/40	30/70	60/40	30/70	60/40

- continued -

- continued -

Physical properties of coating film				
Coating thickness ( $\mu\text{m}$ )	40	40	40	40
Appearance of coating film	A	B	A	B
Gloss	88	80	89	77
Weather resistance	80 %	90 %	82 %	89 %
Flexibility	1T	1T	1T	1T
Adhesive property	100/100	100/100	100/100	100/100
Pulverizability	A	B	A	B
Anti-blocking property	A	A	A	A

- continued -

- continued -

40	40	40	40	40	40	40	40
A	B	A	B	A	B	A	B
85	76	88	78	88	79	89	79
80 %	87 %	60 %	71 %	78 %	87 %	60 %	71 %
1T	1T	1T	1T	1T	1T	1T	1T
100/100	100/100	100/100	100/100	100/100	100/100	100/100	100/100
A	B	A	B	A	B	A	B
A	A	A	A	A	A	A	A

### EXAMPLES 13 to 18

1870  
 1871  
 1872  
 1873  
 1874  
 1875  
 1876  
 1877  
 1878  
 1879  
 1880  
 1881  
 1882  
 1883  
 1884  
 1885  
 1886  
 1887  
 1888  
 1889  
 1890  
 1891  
 1892  
 1893  
 1894  
 1895  
 1896  
 1897  
 1898  
 1899  
 1900  
 1901  
 1902  
 1903  
 1904  
 1905  
 1906  
 1907  
 1908  
 1909  
 1910  
 1911  
 1912  
 1913  
 1914  
 1915  
 1916  
 1917  
 1918  
 1919  
 1920  
 1921  
 1922  
 1923  
 1924  
 1925  
 1926  
 1927  
 1928  
 1929  
 1930  
 1931  
 1932  
 1933  
 1934  
 1935  
 1936  
 1937  
 1938  
 1939  
 1940  
 1941  
 1942  
 1943  
 1944  
 1945  
 1946  
 1947  
 1948  
 1949  
 1950  
 1951  
 1952  
 1953  
 1954  
 1955  
 1956  
 1957  
 1958  
 1959  
 1960  
 1961  
 1962  
 1963  
 1964  
 1965  
 1966  
 1967  
 1968  
 1969  
 1970  
 1971  
 1972  
 1973  
 1974  
 1975  
 1976  
 1977  
 1978  
 1979  
 1980  
 1981  
 1982  
 1983  
 1984  
 1985  
 1986  
 1987  
 1988  
 1989  
 1990  
 1991  
 1992  
 1993  
 1994  
 1995  
 1996  
 1997  
 1998  
 1999  
 2000  
 2001  
 2002  
 2003  
 2004  
 2005  
 2006  
 2007  
 2008  
 2009  
 2010  
 2011  
 2012  
 2013  
 2014  
 2015  
 2016  
 2017  
 2018  
 2019  
 2020  
 2021  
 2022  
 2023  
 2024  
 2025  
 2026  
 2027  
 2028  
 2029  
 2030  
 2031  
 2032  
 2033  
 2034  
 2035  
 2036  
 2037  
 2038  
 2039  
 2040  
 2041  
 2042  
 2043  
 2044  
 2045  
 2046  
 2047  
 2048  
 2049  
 2050  
 2051  
 2052  
 2053  
 2054  
 2055  
 2056  
 2057  
 2058  
 2059  
 2060  
 2061  
 2062  
 2063  
 2064  
 2065  
 2066  
 2067  
 2068  
 2069  
 2070  
 2071  
 2072  
 2073  
 2074  
 2075  
 2076  
 2077  
 2078  
 2079  
 2080  
 2081  
 2082  
 2083  
 2084  
 2085  
 2086  
 2087  
 2088  
 2089  
 2090  
 2091  
 2092  
 2093  
 2094  
 2095  
 2096  
 2097  
 2098  
 2099  
 2100  
 2101  
 2102  
 2103  
 2104  
 2105  
 2106  
 2107  
 2108  
 2109  
 2110  
 2111  
 2112  
 2113  
 2114  
 2115  
 2116  
 2117  
 2118  
 2119  
 2120  
 2121  
 2122  
 2123  
 2124  
 2125  
 2126  
 2127  
 2128  
 2129  
 2130  
 2131  
 2132  
 2133  
 2134  
 2135  
 2136  
 2137  
 2138  
 2139  
 2140  
 2141  
 2142  
 2143  
 2144  
 2145  
 2146  
 2147  
 2148  
 2149  
 2150  
 2151  
 2152  
 2153  
 2154  
 2155  
 2156  
 2157  
 2158  
 2159  
 2160  
 2161  
 2162  
 2163  
 2164  
 2165  
 2166  
 2167  
 2168  
 2169  
 2170  
 2171  
 2172  
 2173  
 2174  
 2175  
 2176  
 2177  
 2178  
 2179  
 2180  
 2181  
 2182  
 2183  
 2184  
 2185  
 2186  
 2187  
 2188  
 2189  
 2190  
 2191  
 2192  
 2193  
 2194  
 2195  
 2196  
 2197  
 2198  
 2199  
 2200  
 2201  
 2202  
 2203  
 2204  
 2205  
 2206  
 2207  
 2208  
 2209  
 2210  
 2211  
 2212  
 2213  
 2214  
 2215  
 2216  
 2217  
 2218  
 2219  
 2220  
 2221  
 2222  
 2223  
 2224  
 2225  
 2226  
 2227  
 2228  
 2229  
 2230  
 2231  
 2232  
 2233  
 2234  
 2235  
 2236  
 2237  
 2238  
 2239  
 2240  
 2241  
 2242  
 2243  
 2244  
 2245  
 2246  
 2247  
 2248  
 2249  
 2250  
 2251  
 2252  
 2253  
 2254  
 2255  
 2256  
 2257  
 2258  
 2259  
 2260  
 2261  
 2262  
 2263  
 2264  
 2265  
 2266  
 2267  
 2268  
 2269  
 2270  
 2271  
 2272  
 2273  
 2274  
 2275  
 2276  
 2277  
 2278  
 2279  
 2280  
 2281  
 2282  
 2283  
 2284  
 2285  
 2286  
 2287  
 2288  
 2289  
 2290  
 2291  
 2292  
 2293  
 2294  
 2295  
 2296  
 2297  
 2298  
 2299  
 2300  
 2301  
 2302  
 2303  
 2304  
 2305  
 2306  
 2307  
 2308  
 2309  
 2310  
 2311  
 2312  
 2313  
 2314  
 2315  
 2316  
 2317  
 2318  
 2319  
 2320  
 2321  
 2322  
 2323  
 2324

TABLE 4

	Ex. 1	Ex. 2	Ex. 13	Ex. 14
Components of powder coating composition (part by weight)				
Polyester polymer (I)				
I-1	41.8	23.0		
I-2			41.6	22.9
I-3				
I-5				
Fluorine-containing polymer (II)				
II-1	17.9	34.5	17.9	34.5
II-3				
II-5				
Curing agent				
B1530	9.8	12.0	10.0	12.1
TGIC				
Pigment	30	30	30	30
Leveling agent	0.5	0.5	0.5	0.5
(I)/(II)	70/30	40/60	70/30	40/60

- continued -

- continued -

Ex. 15	Ex. 16	Ex. 17	Ex. 18	Ex. 9	Ex. 10
		41.8	23.0		
42.0	23.0				
				45.2	26.1
18.0	34.6				
		17.9	34.5		
				19.4	39.2
9.5	11.9	9.8	12.0		
				4.9	4.2
30	30	30	30	30	30
0.5	0.5	0.5	0.5	0.5	0.5
70/30	40/60	70/30	40/60	70/30	40/60

- continued -



- continued -

Physical properties of coating film				
Coating thickness ( $\mu\text{m}$ )	40	40	40	40
Appearance of coating film	A	B	A	B
Gloss	88	80	89	81
Weather resistance	80 %	90 %	79 %	88 %
Flexibility	1T	1T	1T	1T
Adhesive property	100/100	100/100	100/100	100/100
Pulverizability	A	B	A	B
Anti-blocking property	A	A	A	A

- continued -

40	40	40	40	40	40	40
A	B	B	B	C	A	B
89	79	70	68	88	79	
75 %	80 %	65 %	75 %	78 %	87 %	
1T	1T	1T	1T	1T	1T	1T
100/100	100/100	100/100	100/100	100/100	100/100	100/100
A	B	A	B	A	B	
A	A	B	B	A	A	A

Thermosetting powder coating compositions for comparison comprising components shown in Table 5 were prepared and coated in the same manner as in Example 1, and various tests were carried out.

- 5 The results are shown in Table 5.

THE UNIVERSITY OF CHICAGO

TABLE 5

	Com. Ex. 1	Com. Ex. 2	Com. Ex. 3	Com. Ex. 4	Com. Ex. 5
Components of powder coating composition (part by weight)					
Polyester polymer (A)					
I-1	62.1				
I-3		61.8			
I-4					22.7
I-5			63.9		
Fluorine-containing polymer (B)					
II-1				54.7	
II-3					34.2
Curing agent					
B1530	7.4	7.7		14.8	12.6
TGIC			5.6		
Pigment	30	30	30	30	30
Leveling agent	0.5	0.5	0.5	0.5	0.5
(I)/(II)	100/ 0	100/ 0	100/ 0	0/ 100	40/ 60
Physical properties of coating film					
Coating thickness (μm)	40	40	40	40	40
Appearance of coating film	A	A	A	D	D
Gloss	90	91	90	65	63
Weather resistance	40 %	31 %	32 %	98 %	48 %
Flexibility	3T	3T	3T	1T	2T
Adhesive property	100/ 100	100/ 100	100/ 100	0/ 100	100/ 100
Pulverizability	A	A	A	D	D
Anti-blocking property	A	A	A	C	B

From the results of Tables 3 to 5, it is seen that the following effects are exhibited.

First when the specific polyester polymer to be used in Invention 2 is used solely (Comparative Examples 1 to 3), weather resistance and flexibility are inferior though an appearance of a coating film is excellent. Also when the specific fluorine-containing polymer comprising a vinyl ester unit which is used in Invention 1 is used solely (Comparative Example 4), though weather resistance is very excellent, adhesive property and storage stability of a powder as well as an appearance of a coating film are inferior. Further in case of a combination use of a fluorine-containing polymer comprising no vinyl ester unit and a general purpose polyester polymer (Comparative Example 5), storage stability is improved, but an appearance of a coating film is inferior and weather resistance is not improved.

On the other hand, in case of a combination use of the specific fluorine-containing polymer (A) to be used in Invention 1 and the polyester polymer (B) (Examples 1 to 12), even when a general purpose polyester polymer is used as the polyester polymer (B) (Examples 7, 8, 11 and 12), weather resistance is improved and an appearance of a coating film is excellent. Further when the specific polyester polymer (I) to be used in Invention 2 is used as the polyester polymer (B) (Examples 1 to 6, 9 and 10), weather resistance and an appearance of a coating film are very excellent and well-balanced.

Also in case of a combination use of the specific polyester polymer (I) to be used in Invention 2 and the fluorine-containing polymer (II), when the specific fluorine-containing polymer (A) comprising a vinyl ester unit which is used in Invention 1 is used as the fluorine-containing

polymer (II), (Examples 13 to 16 and Examples 1, 2, 9 and 10), weather resistance and an appearance of a coating film are very excellent and well-balanced. Even when the specific fluorine-containing polymer (A) is not used (Examples 17 and 18), both of weather resistance and an appearance of a coating film and further pulverizability are excellent as compared with Comparative Example 5 in which the specific polyester polymer (I) is not used.

#### INDUSTRIAL APPLICABILITY

According to the present invention, weather resistance and an appearance of a coating film, for example, gloss and smoothness which are conflicting properties in the thermosetting powder coating composition can be enhanced and well balanced.

## CLAIMS

1. A thermosetting powder coating composition which comprises a fluorine-containing polymer (A) comprising a fluoroolefin unit and a vinyl ester unit and having a crosslinkable reactive group, a polyester polymer (B) having a crosslinkable reactive group, and a curing agent.
2. The powder coating composition of Claim 1, wherein a molecular weight of the vinyl ester unit in said fluorine-containing polymer (A) is from 70 to 400.
3. The powder coating composition of Claim 1 or 2, wherein said vinyl ester unit is vinyl versatate unit and/or vinyl benzoate unit.
4. A thermosetting powder coating composition which comprises a polyester polymer (I) containing isophthalic acid and/or 1,4-cyclohexane dicarboxylic acid as the essential component and having a crosslinkable reactive group, a fluorine-containing polymer (II), and a curing agent.
5. The powder coating composition of Claim 4, wherein said polyester polymer (I) is a polyester polymer containing isophthalic acid and/or 1,4-cyclohexane dicarboxylic acid as a polybasic acid component and a polyhydric alcohol as a polyol component, in which hydrogen at  $\beta$  position has been substituted by an alkyl group.

# ABSTRACT

In the thermosetting powder coating composition prepared by a combination use of a fluorine-containing polymer and a polyester polymer and containing a curing agent, the fluorine-containing polymer (A) comprising a fluoroolefin unit and a vinyl ester unit and having a crosslinkable reactive group is used as the fluorine-containing polymer or the polyester polymer (I) containing isophthalic acid and/or 1,4-cyclohexane dicarboxylic acid as essential components and having a crosslinkable reactive group is used as the polyester polymer. By the use of this composition, weather resistance and an appearance of a coating film, for example, gloss and smoothness which are conflicting properties in the thermosetting powder coating composition can be enhanced and well balanced.



# Declaration and Power of Attorney for Patent Application

特許出願宣言書及び委任状

## Japanese Language Declaration

日本語宣言書

私は、以下に記名された発明者として、ここに下記の通り宣言する。

私の住所、郵便の宛先及び国籍は、私の氏名の後に記載された通りである。

下記の名称の発明について、特許請求範囲に記載され、且つ特許が求められている発明主題に関して、私は、最初、最先且つ唯一の発明者である(唯一の氏名が記載されている場合)か、或いは最初、最先且つ共同発明者である(複数の氏名が記載されている場合)と信じている。

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

THERMOSETTING POWDER COATING  
COMPOSITION

上記発明の明細書はここに添付されているが、下記の欄がX印でチェックされている場合は、この限りでない:

☐ \_\_\_\_月 \_\_\_\_日に出願され、PCT国際出願番号を  
\_\_\_\_とし、かつ \_\_\_\_月 \_\_\_\_日に出願された  
米国出願番号は\_\_\_\_であり、  
\_\_\_\_月 \_\_\_\_日に補正された出願(該当する場合)

the specification of which is attached hereto unless the following box is checked:

☐ was filed on \_\_\_\_ as PCT  
International Application No. \_\_\_\_ and  
subsequently on \_\_\_\_ as United States  
Application No. \_\_\_\_ and was amended on  
(if applicable).

私は、上記の補正書によって補正された特許請求範囲を含む上記明細書を検討し、且つ内容を理解していることをここに表明する。

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

私は、連邦規則法典第37編1.56に定義されている特許性について重要な情報を開示する義務があることを認める。

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

# Japanese Language Declaration

(日本語宣言書)

私は、ここに、下記に記載した外国での特許出願または発明者証の出願、或いは米国以外の少なくとも一カ国を指定している米国法典第35編365条(a)項によるPCT国際出願について、同第119条(a)-(d)項又は第365条(b)項に基づいて優先権を主張するとともに、優先権を主張する本出願の出願日よりも前の出願日を有する外国での特許出願または発明者証の出願、或いはPCT国際出願については、いかなる出願も、下記の枠内をチェックすることにより示した。

## Prior Foreign Applications 外国での先行出願

(Number) (番号)	(Country) (国名)
(Number) (番号)	(Country) (国名)
(Number) (番号)	(Country) (国名)

私は、ここに、下記のいかなる米国仮特許出願についても、その米国法典第35編119条(e)項の利益を主張する。

(Application No.) (出願番号)	(Filing Date) (出願日)
-----------------------------	------------------------

私は、ここに、下記のいかなる米国出願についても、その米国法典第35編第120条に基づく利益を主張し、また米国を指定するいかなるPCT国際出願についても、その同第365条(c)に基づく利益を主張する。また、本出願の各特許請求の範囲の主題が、米国法典第35編第112条第1段に規定された態様で、先行する米国出願またはPCT国際出願に開示されていない場合においては、その先行出願の出願日と本国内出願日またはPCT国際出願日との間の期間中に入手された情報で、連邦規則法典第37編規則1.56に定義された特許性に関わる重要な情報について開示義務があることを承認する。

(Application No.) (出願番号)	(Filing Date) (出願日)
-----------------------------	------------------------

私は、ここに表明された私自身の知識にかかわる陳述が真実であり、且つ情報と信ずることに基づく陳述が、真実であると信じられることを宣言し、さらに、故意に虚偽の陳述などを行った場合は、米国法典第18編第1001条に基づき、罰金または拘禁、もしくはその両方により処罰され、またそのような故意による虚偽の陳述は、本出願またはそれに対して発行されるいかなる特許も、その有効性に問題が生ずることを理解した上で、陳述が行われたことを、ここに宣言する。

I hereby claim foreign priority under Title 35, United States Code, Section 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

## Priority Claimed 優先権の主張

<input type="checkbox"/>	<input type="checkbox"/>
YES あり	NO なし
<input type="checkbox"/>	<input type="checkbox"/>
YES あり	NO なし
<input type="checkbox"/>	<input type="checkbox"/>
YES あり	NO なし

(Day/Month/Year Filed) (出願日/月/年)
(Day/Month/Year Filed) (出願年月日)
(Day/Month/Year Filed) (出願年月日)

I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below.

(Application No.) (出願番号)	(Filing Date) (出願日)
-----------------------------	------------------------

I hereby claim the benefit of Title 35, United States Code Section 120 of any United States application(s), or 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code Section 112, I acknowledge the duty to disclose any material information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

(Status: Patented, Pending, Abandoned) (現況: 特許許可済、係属中、放棄済)
---

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

# Japanese Language Declaration

(日本語宣言書)

委任状: 私は、本出願を審査する手続きを行い、且つ米国特許商標庁との全ての業務を遂行するために、記名された発明者として、下記の弁護士及び/または弁理士を任命する。(氏名及び登録番号を記載すること)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith (list name and registration number)

John H. Mion, Reg. No. 18,879; Thomas J. Macpeak, Reg. No. 19,292; Robert J. Seas, Jr., Reg. No. 21,092; Darryl Mexic, Reg. No. 23,063; Robert V. Sloan, Reg. No. 22,775; Peter D. Olexy, Reg. No. 24,513; J. Frank Osha, Reg. No. 24,625; Waddell A. Biggart, Reg. No. 24,861; Louis Gubinsky, Reg. No. 24,835; Neil B. Siegel, Reg. No. 25,200; David J. Cushing, Reg. No. 28,703; John R. Inge, Reg. No. 26,916; Joseph J. Ruch, Jr., Reg. No. 26,577; Sheldon I. Landsman, Reg. No. 25,430; Richard C. Turner, Reg. No. 29,710; Howard L. Bernstein, Reg. No. 25,665; Alan J. Kasper, Reg. No. 25,426; Kenneth J. Burchfiel, Reg. No. 31,333; Gordon Kit, Reg. No. 30,764; Susan J. Mack, Reg. No. 30,951; Frank L. Bernstein, Reg. No. 31,484; Mark Boland, Reg. No. 32,197; William H. Mandir, Reg. No. 32,156; Brian W. Hannon, Reg. No. 32,778; Abraham J. Rosner, Reg. No. 33,276; Bruce E. Kramer, Reg. No. 33,725; Paul F. Neils, Reg. No. 33,102; Brett S. Sylvester, Reg. No. 32,765; Robert M. Masters, Reg. No. 35,603; George F. Lehnigk, Reg. No. 36,359; John T. Callahan, Reg. No. 32,607; Steven M. Gruskin, Reg. No. 36,818; Peter A. McKenna, Reg. 38,551 and Edward F. Kenehan, Jr., Reg. 28,962

書類送付先:

Send Correspondence to:

SUGHRUE, MION, ZINN, MACPEAK & SEAS, PLLC  
2100 Pennsylvania Avenue, N.W., Washington, D.C. 20037-3213

直通電話連絡先: (名称及び電話番号)

Direct Telephone Calls to: (name and telephone number)

(202)293-7060

Full name of sole or first inventor

唯一又は第一発明者名

01- Ryuji IWAKIRI (deceased)

Inventor's signature

発明者の署名

MIYUKI IWAKIRI

Date

日付

June 6, 2001

by Miyuki Iwakiri,  
as Legal Representative of Ryuji Iwakiri, Deceased

Residence

住所

Residence of Miyuki Iwakiri: Minoo-shi, OSAKA 562-0005 JAPAN  
Residence of Ryuji Iwakiri (deceased): Settsu-shi, OSAKA 566-8585 JAPAN

Citizenship

国籍

Citizenship of Miyuki Iwakiri: Japanese  
Citizenship of Ryuji Iwakiri (deceased): Japanese

Post office address

郵便の宛先

Post office address of Miyuki Iwakiri:  
11-31-102, Niina 4-chome, Minoo-shi, OSAKA 562-0005 JAPAN  
Post office address of Ryuji Iwakiri (deceased):  
c/o Yodogawa-seisakusho, DAIKIN INDUSTRIES, LTD.  
1-1, Nishihitotsuya, Settsu-shi, OSAKA 566-8585 JAPAN

Full name of second joint inventor, if any

第二共同発明者名 (該当する場合)

20 Ryoichi FUKAGAWA

Second inventor's signature

第二発明者の署名

Ryoichi Fukagawa

Date

日付

June 6, 2001

Residence

住所

Settsu-shi, OSAKA 566-8585 JAPAN

Citizenship

国籍

Japanese

Post office address

郵便の宛先

c/o Yodogawa-seisakusho, DAIKIN INDUSTRIES, LTD.  
1-1, Nishihitotsuya, Settsu-shi, OSAKA 566-8585 JAPAN

(第三以降の共同発明者についても同様に記載し、署名をすること。)

(Supply similar information and signature for third and subsequent joint inventors.)

# Japanese Language Declaration

(日本語宣言書)

Full name of third joint inventor, if any 第三共同発明者名(該当する場合)		<i>Keisuke TANO</i>	
Third inventor's signature 第三発明者の署名		Date 日付	June 6, 2001
Residence 住所		Settsu-shi, <u>OSAKA</u> 566-8585 JAPAN <i>SPX</i>	
Citizenship 国籍		Japanese	
Post office address 郵便の宛先		c/o Yodogawa-seisakusho, DAIKIN INDUSTRIES, LTD. 1-1, Nishihitotsuya, Settsu-shi, OSAKA 566-8585 JAPAN	
Full name of fourth joint inventor, if any 第四共同発明者名(該当する場合)		<i>Daisuke TANIZAWA</i>	
Fourth inventor's signature 第四発明者の署名		Date 日付	June 6, 2001
Residence 住所		Settsu-shi, <u>OSAKA</u> 566-8585 JAPAN <i>SPX</i>	
Citizenship 国籍		Japanese	
Post office address 郵便の宛先		c/o Yodogawa-seisakusho, DAIKIN INDUSTRIES, LTD. 1-1, Nishihitotsuya, Settsu-shi, OSAKA 566-8585 JAPAN	
Full name of fifth joint inventor, if any 第五共同発明者名(該当する場合)		<i>Nobuhiko TSUDA</i>	
Fifth inventor's signature 第五発明者の署名		Date 日付	June 6, 2001
Residence 住所		Settsu-shi, <u>OSAKA</u> 566-8585 JAPAN <i>SPX</i>	
Citizenship 国籍		Japanese	
Post office address 郵便の宛先		c/o Yodogawa-seisakusho, DAIKIN INDUSTRIES, LTD. 1-1, Nishihitotsuya, Settsu-shi, OSAKA 566-8585 JAPAN	
Full name of sixth joint inventor, if any 第六共同発明者名(該当する場合)			
Sixth inventor's signature 第六発明者の署名		Date 日付	
Residence 住所			
Citizenship 国籍			
Post office address 郵便の宛先			